

HDPE B03949G



Overview

Good processability, chemical resistance, toughness. GAS PHASE

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	0.3	g/10 min	D 1238
Density (g/cm ³)	0.949	g/cm ³	D 792