

HDPE B2H954

High Density Polyethylene - Powder



Overview

This high density polyethylene designed for blow molding and extrusion applications that require high impact strength, high rigidity and chemical resistance. This grade has good ESCR. This grade comes in powder form and includes antioxidants.

Applications

- Top Drums
- High impact resistance
- Jerry Cans
- High rigidity and chemical resistance
- Packaging for dangerous goods
- Good ESCR
- Blow molding applications
- Comes in powder form and includes antioxidants

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	2.0	g/10 min	D 1238
Density (g/cm ³)	0.954	g/cm ³	D 792
Bulk Density	>0.460	g/cm ³	ISO 60
Tensile Modulus, 23°C	1200	MPa	ISO 527-1,-2
Tensile Stress at Yield, 23°C	27.0	MPa	ISO 527-1,-2
Tensile Strain at Yield	9.0	%	ISO 527-1,-2
Tensile Impact Strength	250	KJ/m ²	ISO 8256
Hardness (H 132/30)	52.0	MPa	ISO 2039-1
Vicat Softening Temp. (50°C/h 10n)	132	°C	ISO 306
Vicat Softening Temp. (50°C/h 50n)	80	°C	ISO 306
Heat Deflection Temp. (.45 MPa)	75.0	°C	ISO 75B-1, -2
Heat Deflection Temp. (1.80 MPa)	44.0	°C	ISO 75A-1, -2

Property	Value	Unit	ASTM
Melting Temperature	134	°C	ISO 3146
ESCR, Condition B, F50	12	hrs	ISO 16770

Not intended for use in medical and pharmaceutical applications