HDPE B3H954

StarResin

Overview

High impact resistance, hight rigidity and chemical resistance, good ESCR. POWDER form.

Property	Value	Unit	ASTM
Melt index (condition 190°C/2.16 kg)	3.5 HLMI	g/10 min	D 1238
Density (g/cm³)	0.954	g/cm³	D 792

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.