

LLDPE B3918



Overview

ethylene 1-butene LLDPE resin designed for the blown film. It has good drawdown and films produced from this resin exhibit excellent toughness and tensile properties.

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	3.00	g/10 min	D 1238
Density (g/cm ³)	0.918	g/cm ³	D 792