

LLDPE H2920.SA



Overview

HEXENE LLDPE resin designed for the blown film. It has good drawdown and films produced from this resin exhibit excellent toughness and tensile properties. This resin contains an antiblock and slip additives. WITH SLIP & BLOCK

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	2.00	g/10 min	D 1238
Density (g/cm ³)	0.920	g/cm ³	D 792