

# LDPE L03920



## Overview

- Superior Toughness
- Excellent Impact
- Excellent Puncture
- Excellent Bubble Stabilizer for LLDPE

This grade can be provided with Antiblock (L03920.A) or without slip and antiblock (L03920.B)

## Applications

- Industrial Shrink Film
- Agriculture Films
- Heavy Duty Sheeting
- Bundling Film

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	0.25	g/10 min	D 1238
Density (g/cm <sup>3</sup> )	0.920	g/cm <sup>3</sup>	D 792
Haze	11	%	D1003
Specular Gloss @ 45°	50		D2457
Dart Drop Impact	230	g/mil	D1709
Elmendorf Tear Strength MD/TD	290/170	gm/mil	D1922
Tensile Strength at Break MD/TD	4600/4100	psi	D882
Elongation at Break MD/TD	310/600	%	D882
Secant Modulus, 1% Secant MD/TD	24500/27500	psi	D882