

Overview

Good Processability.

Good Optics.

Good Toughness.

Excellent Bubble Stabilizer for LLDPE.

Applications

- Coallation Shrink Film
- Form Fill and Seal
- Medium Duty Shrink
- Lamination Film

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	0.7	g/10 min	D 1238
Density (g/cm ³)	0.920	g/cm ³	D 792
Haze	10	%	ASTM D1003
Specular Gloss @ 45°	59		ASTM D2457
Dart Impact	120	gm/mil	ASTM D1709
Elmendorf Tear MD/TD	220/200	mg/mil	ASTM D1922
Tensile at Break MD/TD	3400/2400	psi	ASTM D882
Elongation at Break MD/TD	170/490	%	ASTM D882
1% Secant Modulus MD/TD	25000/31500	psi	ASTM D882

A film specimen with a 2.0mil thickness was used for testing.

This grade can be provided with Antiblock (L07920.A) or without slip and antiblock (L07920.B).

Regulatory - This material complies with FDA regulations in 21 CFR, section 177.1520.