LDPE E6918

StarResin

Overview

Low Oder & Taste
Excellent Processability
Excellent Draw-down
Minimal Neck-In
Regulatory - This material complies with FDA regulations in 21 CFR, section 177.1520.

Applications

- Paper and Board Coating
- Laminations
- Dry Foods Packaging
- Medical Packaging

Property	Value	Unit	ASTM
Melt index (condition 190°C/2.16 kg)	6	g/10 min	D 1238
Density (g/cm³)	0.918	g/cm³	D 792
Melting Point	230/110	°F / °C	ASTM D3418
Vicat Softening Temperature	207/97	°F / °C	ASTM D1525
Water Vapor Transmission Rate	1.2	g/100in2/day	ASTM F1249
Oxygen Transmission Rate	500	cm3/100in2/day	ASTM D3985

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.