

## Overview

Low order & tate, excellent processability, excellent draw-down

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	8	g/10 min	D 1238
Density (g/cm <sup>3</sup> )	0.918	g/cm <sup>3</sup>	D 792