

Overview

PP 35900 is a homopolymer resin designed for injection molding applications requiring high melt ow rate.

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	35	g/10 min	D 1238