

LLDPE B1918.SA

Linear Low Density Polyethylene



Overview

LLDPE B1918.SA is butene LLDPE blown film resin. It has good drawdown and films produced from this resin exhibit excellent toughness and tensile properties.

Applications

- General Purpose
- Can Liners
- Food Packaging
- Commercial Packaging

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	1.00	g/10 min	D 1238
Density (g/cm ³)	0.918	g/cm ³	D 792
Haze	18	%	D1003
Gloss (45°)	40		D2457
Dart Drop Impact	110	gm/mil	D1709A
Elmendorf Tear Strength MD/TD	140/340	gm/mil	D1922
Tensile Strength at Break MD/TD	6500/4600	psi	D882
Elongation at Break MD/TD	570/730	%	D882
Secant Modulus, 1% Secant MD/TD	27000/27500	psi	D882

FDA Status - This resin complies with FDA 21 CFR 177.1520.

This material has slip and antiblock.