

# LLDPE 50924G

Linear Low Density Polyethylene



## Overview

LLDPE 50924 G is a narrow molecular weight butene copolymer in granular form. It is intended for compounding and applications requiring easy processability in thin walled parts. It offers excellent toughness and tear resistance properties in freezer applications for food packaging.

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	50.00	g/10 min	D 1238
Density (g/cm <sup>3</sup> )	0.926	g/cm <sup>3</sup>	D 792
Flexural Modulus, 1% Secant	68000	psi	D790B
Flexural Modulus, 2% Secant	61000	psi	D790B
Tensile Strength at Yield	1700	psi	D638
Tensile Elongation at Yield	90	%	D638
Peak Melting Temperature	252	°F	D3418
Vicat Softening Temperature	185	°F	D1525
ESCR 100% Igepal, F50	30	hrs	D1693B