

LDPE LDF 700-B

Low Density Polyethylene



Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	0.25	g/10 min	D 1238
Density (g/cm ³)	0.920	g/cm ³	D 792
Dart Drop Impact	140	g	D1709A
Tensile Strength (MD / TD)	4200 / 2900	psi	D882
Elongation (MD / TD)	105 / 400	%	D882
1% Secant Modulus (MD / TD)	27,000 / 32,000	psi	D882
Haze	30	%	D1003

Additives: Medium Antiblock (3000 PPM)