

EVA 400.28

Ethylene-Vinyl Acetate



Overview

EVA 400.28 has excellent compatibility with hydrocarbons, most waxes, and natural tackifiers, and it is designed for making hot melt adhesives.

Applications

- Adhesives
- Sealants
- Wax blends
- Industrial sealants

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	400	g/10 min	D 1238
Density (g/cm ³)	0.941	g/cm ³	D 792
Vinyl Acetate Content	28	wt%	
Flexural Modulus – 1% Secant	1900	psi	D790
Elongation at Break	500	%	D638
Tensile Strength at Break	200	psi	D638
Durometer Hardness, Shore A	60		D2240