

LLDPE O2919

Linear Low Density Polyethylene -
Octene



Overview

LLDPE O2919 features exceptional toughness and low gel level.

Applications

- Cast stretch films
- Lamination films
- Co-extrusion

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	2	g/10 min	D 1238
Density (g/cm ³)	0.919	g/cm ³	D 792
Elmendorf Tear Strength	1100	g	D1922
Dart Drop Impact	450	g	D1709A
Gloss	65		D2457
Haze	11	%	D1003