

Overview

MARPOL COPP 35.2 is high melt flow impact polypropylene copolymer resin. It is ideal for injection molding applications that require a good balance of impact stiffness, resistance and processability.

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	35	g/10 min	D 1238
Density (g/cm ³)	0.900	g/cm ³	D 792
Tensile Strength (Yield)	26.2	MPa	D638
Flexural Modulus – 1 % Secant	1,370	MPa	D790A
Notched Izod Impact (23 °C)	110	J/m	D256