

Flexirene FG 23 F



Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	1	g/10 min	D 1238
Density (g/cm ³)	0.918	g/cm ³	D 792

Producer: Versalis