

Overview

Availability: Global  
Description: 98% Post Industrial Recycled Content  
Color: Black

Applications

- Profile Extrusion
- Blow Molding

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	0.35	g/10 min	D 1238
Density (g/cm <sup>3</sup> )	0.955	g/cm <sup>3</sup>	D 792
Flexural Modulus	170,000	psi	ASTM D790
Tensile Strength	4,100	psi	ASTM D638
Recycled Content	Recycled Content	%	PIR

Producer: Aspect