

Overview

Availability: Global
Features: 100% PCR
Color: Clear/Natural
Shape: Die cut (spherical) resin

Applications

- General Extrusion, Blow Molding, Film Extrusion

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	0.35 – 0.65	g/10 min	D 1238
Density (g/cm ³)	0.950 - 0.960	g/cm ³	D 792
Ash	< 1	wt. %	ISO 3451
L*	72+	value	ISO 11664

Producer: Aspect

□ ISO 14001:2015 Compliant - Produced from post-consumer goods □ California Prop 65 Compliant – Lead and Cadmium These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee as conditions and methods of use are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.