

Aspect Natural FDA PP PIR 35

100% Recycled Natural Polypropylene



Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	35 - 40	g/10 min	D 1238
Density (g/cm ³)	0.902	g/cm ³	D 792
Flexural Modulus	140,000 - 169,000	psi	D790
Tensile Strength	3600 - 3700	psi	D638
Notched Izod	1.7 - 2.7	ft-lb/in	D256
FDA Recycled Content	100	%	

Producer: Aspect