

Aspect Black HIPS Repro 6.2



Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	6.0	g/10 min	D 1238
Density (g/cm ³)	N/A	g/cm ³	D 792
Tensile Stress at Yield	28.1	MPa	D3759
Notched Izod Impact Strength	1.82	ft-lb/in ²	D256
Elongation	51	%	

Producer: Aspect