

Overview

SHA7260 is a high-density polyethylene, developed for the injection molding, easy to process and with high productivity. This resin has a good melt flow with high rigidity and hardness. Its narrow molar mass distribution results in a low tendency to warpage. The minimum biobased carbon content of this grade is 94%, determined according to ASTM D6866.

Applications

- Caps, Thin wall parts, Houseware, toys

Property	Value	Unit	ASTM
Melt index (condition 230°C/2.16 kg)	20	g/10 min	D 1238
Density (g/cm ³)	0.955	g/cm ³	D 792
Tensile Strength at Yield (a)	29	MPa	D 638
Elongation at Yield (a)	7.2	%	D 638
Flexural Modulus - 1% Secant (b)	1250	MPa	D 2240
Shore D Hardness (c)	20	J/m	D 256
Deflection Temperature under Load at 0.455 MPa (b)	67	°C	D 648
Vicat So ening Temperature at 10 N (b)	121	°C	D 1525

Producer: Braskem

1 Test specimens from compression molded plaque according to ASTM D4703. Plaque Thickness: a) 2mm. b) 3mm c) 6mm. NB = No break. Final Remarks: 1. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product. 2. For regulatory information of the product, please refer to Regulatory Document or contact our Technical Assistance Area. 3. For information about safety, handling, individual protection, first aids and waste disposal, please refer to MSDS. 4. The mentioned values in this report can be changed at any moment without Braskem previous communication.